

Polybond[®] 3200

Polymer Modifier

Polybond[®] 3200 is a maleic anhydride modified polypropylene homopolymer.

CAS Number 9003-07-0

Typical Physical Properties of PRODUCT[®] 3200

Property	Typical Value	Test Based On
Appearance	Off-white Pellet	Visual
Melt Flow Rate @ 190°C, 2.16Kg	115 g/10 min	ASTM D-1238
Maleic Anhydride Content	High*	ASTM D-6047
Specific Gravity @ 23°C	0.91 g/cm ³	ASTM D-792
Bulk Density	0.6 g/cm ³	ASTM D1895B
Melting Point	157°C	DSC

* High = Maleic Anhydride Content typically in the range of 0.8 to 1.2%.

Applications

Feature	Benefit
High efficiency coupling agent for glass-filled Polypropylene	Improved physical properties including strength properties Lower addition levels can be used than with other Polybond [®] products
Coupling agent for Cellulose fiber-filled Polypropylene	Reduced water uptake & higher flexural/tensile strengths
Compatibilizer for Polypropylene/Polyamide Blends	Improved processing & enhanced strength properties
Coupling agent for mineral filler in Polypropylene	Improves strength & impact properties
Well suited for tie-layers	Low viscosity & high level of functionality

Food Contact

For details please contact Addivant[™] Regulatory Affairs

Regulatory Status

The components of Polybond[®] 3200 are listed on USA TSCA inventory. For information on other inventory listings, see Section 15 (Regulatory Information) of the MSDS for Polybond[®] 3200.

The information contained herein relates to a specific Addivant[™] product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of Addivant[™] standard terms and conditions of sale under which the product is sold by Addivant[™]. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND ANY AND ALL SUCH REPRESENTATIONS AND WARRANTIES ARE HEREBY EXPRESSLY DISCLAIMED. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

Addivant[™] is a trademark of Addivant USA, LLC or one of its affiliates.
Copyright © 2013 Addivant USA, LLC. All rights reserved.

Storage & Handling Precautions

Keep **Polybond**[®] **3200** dry prior to processing. Loss of anhydride functionality may occur due to conversion to acid groups by reaction with atmospheric moisture. Tie liners of open gaylords, when not in use to prevent exposure to moisture. If exposure occurs, **Polybond**[®] **3200** can be dried in a hopper dryer or oven for three hours at 105°C to remove moisture.

A slight pungent odor is normal during processing of **Polybond 3200**. Purge equipment with polypropylene before and after running **Polybond**[®] **3200**.

For additional handling and toxicological information consult the Addivant Material Safety Data Sheet

The information contained herein relates to a specific Addivant[™] product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of Addivant[™] standard terms and conditions of sale under which the product is sold by Addivant[™]. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND ANY AND ALL SUCH REPRESENTATIONS AND WARRANTIES ARE HEREBY EXPRESSLY DISCLAIMED. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

Addivant[™] is a trademark of Addivant USA, LLC or one of its affiliates.

Copyright © 2013 Addivant USA, LLC. All rights reserved.